

EN: This Datasheet is presented by the manufacturer.

Please visit our website for pricing and availability at www.hestore.hu.

Surface Mount Adhesive

Product Code: SMA

PRODUCT DESCRIPTION

Electrolube Surface Mount Adhesive is a heat curable, one-part thixotropic adhesive. It has high uncured green strength and a fast cure cycle with medium bond strength.

PRODUCT USE

For holding components in place during soldering operations in surface mount assemblies.

FEATURES

- * High 'green strength' i.e. excellent 'stickiness' ensures components do not move during handling before curing has taken place.
- * Thixotropic properties give high dot profile.
- * Excellent mechanical strength.
- * Not affected by UV light so that assembly operations can be carried out in normal conditions of light.
- * Resistant to PCB cleaning solvents.
- * High dielectric strength.
- * Long term stability after cure cycle.
- * Fast cure at 120°C or longer cure at 90°C for component safety.
- * Single part system.
- * Flexible in cured state to ensure components are not stressed.
- * Medium strength cured bond allows component removal for rework.

TYPICAL PROPERTIES

Colour: Red

Consistency: Thixotropic Paste Viscosity: 145,000 cPs Filler diameter: < 10 microns

Hardness (shore): 85

Cure: 60 secs @ 150°C

3-4 mins @ 120°C 30 mins @ 90°C

Working temperature range after curing: -40°C to +130°C



TECHNICAL



Copyright Electrolube 2004

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



Surface Mount Adhesive - Page 2

Volume Resistivity: 1×10^{16} Ohms/cm Dielectric constant: ~ 3.5 at 1khz

PACKAGING

ORDER CODE

10ml Luer Lock Syringe SMA10SL

STORAGE CONDITIONS

The typical shelf life of this product is as follows:-

12 months from date of manufacture if stored between 0-5°C.

9 months from date of manufacture if stored below 20°C.

TECHNICAL DATA SHEET



Copyright Electrolube 2004

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

